

TECHNICAL DATA SHEET

USC Aerosol Under Coating

TECHNICAL CALLS: 1-855-746-4872 (1-855-RING USC)



DESCRIPTION: An aerosol paintable undercoating for all vehicle undercarriages. Forms a rubberized skin that reduces road noise and protects metal from salt corrosion and road debris. Dries fast and does not sag. Does not 'bleed-thru' when topcoated with other aerosol paints. Not recommended for use under professional automotive single stage urethanes and basecoats.

PART NUMBER: 51030



PRODUCT USES:

- Panel & fender undersides
- Hoods & decks
- Trunk interiors
- Section repairs
- Weld joints
- Rust holes
- All chassis parts

Packaging:

UPC Code	037307510307
Cans per case	12
Shipping weight per case	19.6 lbs.
Container	20 fluid ounce can
Label weight	18 ounces (511 grams)
Shipping Classification	Consumer Commodity ORM-D UN 1950
Hazard Class	2.1

Properties:

Flammability	"Extremely Flammable"
Flash point	-4o F
Specific Gravity	0.80
Solids Content	~60%
VOC content	~39%, cannot exceed 40%
MIR value	~0.99
HAPs content	18%
Storage Temperature	40-90F
Application Temperature	50-100F
Durability	Very Good
Abrasion Resistance	Very Good
Heat Resistance	300o F
Gasoline Resistance	No
Resin System	Petroleum Asphalt
Shelf life	Guaranteed for 2 years

Dry Time*:

To touch	10 minutes
To handle	6 hours

*At 72o F, 50% humidity,
1.5 mil thickness

**Curing/Recoat time is extended with
multiple coats and excessively thick
coats**

Gloss*:

Low Lustre, 15-25

*as measured on a 600 gloss meter